

# LOCTITE<sup>®</sup> AA 3107<sup>™</sup>

Known as LOCTITE<sup>®</sup> 3107<sup>™</sup>  
January 2015

## PRODUCT DESCRIPTION

LOCTITE<sup>®</sup> AA 3107<sup>™</sup> provides the following product characteristics:

<b>Technology</b>	Acrylic
<b>Chemical Type</b>	Acrylated urethane
<b>Appearance (uncured)</b>	Transparent light yellow liquid <sup>LMS</sup>
<b>Fluorescence</b>	Positive under UV light <sup>LMS</sup>
<b>Components</b>	One component - requires no mixing
<b>Viscosity</b>	Low
<b>Cure</b>	Ultraviolet (UV)/ visible light
<b>Cure Benefit</b>	Production - high speed curing
<b>Application</b>	Bonding or Potting
<b>Flexibility</b>	Enhances load bearing & shock absorbing characteristics of the bond area.

LOCTITE<sup>®</sup> AA 3107<sup>™</sup> is designed primarily for bonding heavily plasticized PVC. This product has shown good adhesion to other thermoplastics, such as polycarbonate and ABS.

## TYPICAL PROPERTIES OF UNCURED MATERIAL

Specific Gravity @ 25 °C	1.09
Refractive Index	1.47
Flash Point - See SDS	
Viscosity, Brookfield - RVT, 25 °C, mPa·s (cP):	
Spindle 1, speed 10 rpm,	400 to 650 <sup>LMS</sup>

## TYPICAL CURING PERFORMANCE

LOCTITE<sup>®</sup> AA 3107<sup>™</sup> can be cured by exposure to UV and/or visible light of sufficient intensity. To obtain full cure on surfaces exposed to air, radiation @ 220 to 260 nm is also required. The speed of cure will depend upon the UV intensity and spectral distribution of the light source, the exposure time and the light transmittance of the substrates.

## Stress Cracking

Liquid adhesive is applied to a polycarbonate bar 6.4 cm by 13 mm by 3 mm which is then flexed to induce a known stress level.

Stress Cracking, ASTM D 3929, minutes:  
12 N/mm<sup>2</sup> stress on bar >15

## Tack Free Time

Tack Free Time is the time required to achieve a tack free surface

Tack Free Time, seconds:

Zeta<sup>®</sup> 7400 light source, Metal Halide bulb (Indium):

30 mW/cm <sup>2</sup> , measured @ 400 nm	80 to 90
50 mW/cm <sup>2</sup> , measured @ 400 nm	70 to 80

Electrodeless, V bulb:

30 mW/cm <sup>2</sup> , measured @ 365 nm	5 to 10
50 mW/cm <sup>2</sup> , measured @ 365 nm	5 to 10
100 mW/cm <sup>2</sup> , measured @ 365 nm	5 to 10

Electrodeless, H bulb:

30 mW/cm <sup>2</sup> , measured @ 365 nm	5 to 10
50 mW/cm <sup>2</sup> , measured @ 365 nm	5 to 10
100 mW/cm <sup>2</sup> , measured @ 365 nm	<5

Electrodeless, D bulb:

50 mW/cm <sup>2</sup> , measured @ 365 nm	20 to 30
100 mW/cm <sup>2</sup> , measured @ 365 nm	10 to 20

Medium Pressure Hg Arc bulb, Zeta<sup>®</sup> 7200 light source:

50 mW/cm <sup>2</sup> , measured @ 365 nm	10 to 20
100 mW/cm <sup>2</sup> , measured @ 365 nm	10 to 20

**Fixture Time**

Fixture time is defined as the time to develop a shear strength of 0.1 N/mm<sup>2</sup>.

UV Fixture Time, Glass microscope slides, seconds:

Black light, Zeta® 7500 light source:  
6 mW/cm<sup>2</sup>, measured @ 365 nm ≤10<sup>LMS</sup>

UV Fixture Time, Polycarbonate, seconds:

Zeta® 7400 light source, Metal Halide bulb (Indium):  
30 mW/cm<sup>2</sup>, measured @ 400 nm <5  
50 mW/cm<sup>2</sup>, measured @ 400 nm <5

Electrodeless, V bulb:

30 mW/cm<sup>2</sup>, measured @ 365 nm <5  
50 mW/cm<sup>2</sup>, measured @ 365 nm <5

Electrodeless, H bulb:

30 mW/cm<sup>2</sup>, measured @ 365 nm <5  
50 mW/cm<sup>2</sup>, measured @ 365 nm <5

Electrodeless, D bulb:






50 mW/cm<sup>2</sup>, measured @ 365 nm 20 to 30  
100 mW/cm<sup>2</sup>, measured @ 365 nm 10 to 20

Medium Pressure Hg Arc bulb, Zeta® 7200 light source:

50 mW/cm<sup>2</sup>, measured @ 365 nm 10 to 20  
100 mW/cm<sup>2</sup>, measured @ 365 nm 10 to 20

**Depth of Cure vs. Irradiance (365 nm)**

The graphs below show the increase in depth of cure with time at 30 mW/cm<sup>2</sup> - 100 mW/cm<sup>2</sup> as measured from the thickness of the cured product formed in a 9.5mm trough.

**Curing System: Electrodeless, V bulb****Curing System: Metal Halide (Iron)****Curing System: Electrodeless, H bulb****Curing System: Electrodeless, D bulb****Curing System: Hg Arc**

**TYPICAL PROPERTIES OF CURED MATERIAL**

Cured @ 30 mW/cm<sup>2</sup>, measured @ 400 nm for 30 seconds using an indium doped metal halide light source

**Physical Properties:**

Shore Hardness, ISO 868, Durometer D	27
Refractive Index	1.5
Water Absorption, ISO 62, %:	
2 hours in boiling water	3.64
Elongation, at break, ISO 527-3, %	220
UV Depth of Cure, mm	4.0
Tensile Modulus, ISO 527-3	N/mm <sup>2</sup> 25
	(psi) (3,600)
Tensile Strength, at break, ISO 527-3	N/mm <sup>2</sup> 15
	(psi) (2,200)

**Electrical Properties:**

Surface Resistivity, IEC 60093, Ω·cm	2.30×10 <sup>15</sup>
Volume Resistivity, IEC 60093, Ω·cm	9.62×10 <sup>14</sup>
Dielectric Breakdown Strength, , kV/mm	31.5
Dielectric Constant / Dissipation Factor, IEC 60250:	
100 Hz	4.52 / 0.05
1 kHz	5.07 / 0.05
1 MHz	3.52 / 0.04

**TYPICAL PERFORMANCE OF CURED MATERIAL****Adhesive Properties**

Cured @ 30 mW/cm<sup>2</sup>, measured @ 400 nm for 30 seconds using an indium doped metal halide light source

Block Shear Strength, ISO 13445:

Polycarbonate to PVC	N/mm <sup>2</sup> ≥6.2 <sup>LMS</sup>
	(psi) (≥899)

**TYPICAL ENVIRONMENTAL RESISTANCE**

Cured @ 30 mW/cm<sup>2</sup>, measured @ 400 nm for 30 seconds using an indium doped metal halide light source

Block Shear Strength, ISO 13445:

Polycarbonate to PVC:  
0.5 mm gap

**Chemical/Solvent Resistance**

Aged under conditions indicated and tested @ 22 °C.

Environment	°C	% of initial strength		
		2 h	24 h	170 h
Air	71	-----	-----	100
Air	93	-----	-----	100
Boiling water	100	95	-----	-----
Water immersion	49	-----	-----	40
Water immersion	87	-----	-----	20
Isopropanol immersion	22	-----	75	-----
Heat/humidity 95% RH	38	-----	-----	60

**GENERAL INFORMATION**

**This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.**

**For safe handling information on this product, consult the Safety Data Sheet (SDS).**

**Directions for use:**

1. This product is light sensitive; exposure to daylight, UV light and artificial lighting should be kept to a minimum during storage and handling.
2. The product should be dispensed from applicators with black feedlines.
3. For best performance bond surfaces should be clean and free from grease.
4. Cure rate is dependent on lamp intensity, distance from light source, depth of cure needed or bondline gap and light transmittance of the substrate through which the radiation must pass.
5. Cooling should be provided for temperature sensitive substrates such as thermoplastics.
6. Plastic grades should be checked for risk of stress cracking when exposed to liquid adhesive.
7. Excess uncured adhesive can be wiped away with organic solvent (e.g. Acetone).
8. Bonds should be allowed to cool before subjecting to any service loads.

**Loctite Material Specification<sup>LMS</sup>**

LMS dated July 30, 2004. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Quality.

**Storage**

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

**Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties.**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

**Conversions**

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$   
 $\text{kV/mm} \times 25.4 = \text{V/mil}$   
 $\text{mm} / 25.4 = \text{inches}$   
 $\mu\text{m} / 25.4 = \text{mil}$   
 $\text{N} \times 0.225 = \text{lb}$   
 $\text{N/mm} \times 5.71 = \text{lb/in}$   
 $\text{N/mm}^2 \times 145 = \text{psi}$   
 $\text{MPa} \times 145 = \text{psi}$   
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$   
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$   
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$   
 $\text{mPa}\cdot\text{s} = \text{cP}$

**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

**Reference 1.2**

Henkel Americas  
+860.571.5100

Henkel Europe  
+49.89.320800.1800

Henkel Asia Pacific  
+86.21.2891.8859

**For the most direct access to local sales and technical support visit: [www.henkel.com/industrial](http://www.henkel.com/industrial)**