

LOCTITE ECCOBOND UV 9060F

July 2012

PRODUCT DESCRIPTION

LOCTITE ECCOBOND UV 9060F provides the following product characteristics:

Technology	Acrylate
Appearance	Translucent light blue
Product Benefits	<ul style="list-style-type: none"> • Fast cure • One component • Cures in shadowed areas • Easy dispensability without stringing • Fluorescent under UV light
Cure	Ultraviolet (UV)/ moisture
Application	Assembly
Typical Package Application	Local protection of WLCSP and BGA on circuit board

LOCTITE ECCOBOND UV 9060F no flow, UV/moisture cure encapsulant is designed for local circuit board protection. This product is fluorescent when viewed with ultraviolet (black) light.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Viscosity, Rheometer, Cone and Plate, mPa·s (cP):

@ 5 s ⁻¹	11,000
@ 50 s ⁻¹	2,100

Shelf Life @ 5°C (from date of manufacture), months 6

Flash Point - See SDS

TYPICAL CURING PERFORMANCE

Recommended UV Cure

Light Source and Condition:

Metal halide doped spectrum UV lamp

Lamp Power, W/in 300

Distance between lamp to substrate, inches 4

Irradiance UVA, EIT puck radiometer, mW/cm² 566

Recommended Dose, seconds 5 to 25

Moisture cures occurs at ambient temperature and humidity.

*Cures at least 0.25 inch under optimum conditions.

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

DMA and TMA tests conducted on samples UV + 7 days moisture (RT, 50% RH) cured.

Hardness, Tg and modulus increases with additional moisture cure.

CTE decreases with additional moisture cure.

Physical Properties

Hardness, Shore D, After initial UV dose of 6.4 J/cm², moisture cure condition of 50%RH @ room temperature:

Initial, after UV Cure	15
+ 1 day moisture cure	20
+ 2 days moisture cure	30
+ 3 days moisture cure	50
+ 4 days moisture cure	67
+ 8 days moisture cure	76

Coefficient of Thermal Expansion, TMA, ppm/°C:

Below Tg	81.5
Above Tg	198

Glass Transition Temperature (Tg) by TMA, °C 75

Storage Modulus, DMA:

@ 25 °C	N/mm ²	2,200
	(psi)	(319,000)

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

DIRECTIONS FOR USE

1. Use cotton gloves to handle syringe. Touching the syringe with bare hands may induce thaw voids between the adhesive and inside walls of the syringe.
2. Handle the syringes by the end or, if packaged in bags, by the corner. A warm hand holding a cold syringe can sometimes cause formation of freeze/thaw voids.
3. Complete cleaning of the substrates should be performed to remove contamination such as oxide layers, dust, moisture, salt and oils which can cause poor adhesion or corrosion in a bonded part.
4. Usable shelf life may vary depending on method of application and storage conditions.

THAWING:

1. DO NOT open the container before contents reach 25°C temperature. Any moisture that collects on the warmed up container should be removed prior to opening the container.
2. Once material has reached room temperature, the adhesive should not be re-refrigerated.
3. Voids can form in the syringes if syringes are repeatedly re-refrigerated.
4. Typical thaw/warm-up times for different package sizes are shown below (products stored at -20°C):

@ 25°C, 30 cc syringes, minutes	45 to 60
@ 25°C, 55 cc syringes, hours	2
@ 25°C, 6 ounce cartridges, hours	3

Storage

Store in original, tightly covered containers in clean, dry areas. Storage information may be indicated on the product container labeling.

Optimal Storage : 5 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{psi} \times 145 = \text{N/mm}^2$
 $\text{MPa} = \text{N/mm}^2$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly

recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada, Inc. the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1