



LOCTITE® 3981™

July 2008

PRODUCT DESCRIPTION

LOCTITE® 3981™ provides the following product characteristics:

Technology	Epoxy
Chemical Type	Epoxy
Appearance (uncured)	Translucent, slight amber liquid ^{LMS}
Appearance (cured)	Translucent, slight amber solid ^{LMS}
Fluorescence	Positive under UV light
Components	One component - requires no mixing
Cure	Heat cure
Cure Benefit	Production - high speed curing
Application	Assembly of disposable medical devices.
Key Substrates	Stainless steel and Plastics

LOCTITE® 3981™ is suitable for a wide range of applications that require fast cure, excellent environmental resistance and high adhesion. The product cures rapidly when exposed to temperatures as low as 100 °C and achieves excellent adhesion to plastics, metals and glass. LOCTITE® 3981™ was specifically designed for bonding stainless steel cannulae into hubs, syringes and lancets for needle assemblies. Suitable for use in the assembly of **disposable medical devices**.

ISO-10993

An ISO 10993 Test Protocol is an integral part of the Quality Program for LOCTITE® 3981™. LOCTITE® 3981™ has been qualified to Loctite's ISO 10993 Protocol as a means to assist in the selection of products for use in the medical device industry. Certificates of Compliance are available at www.loctite.com or through the Henkel Loctite Quality Department.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Specific Gravity @ 25 °C	1.14
Flash Point - See MSDS	
Viscosity, Brookfield SSA - RVT, 25 °C, mPa·s (cP):	
Spindle 14, speed 50 rpm	4,000 to 6,000 ^{LMS}

TYPICAL CURING PERFORMANCE

Cure Schedule

Typical cure times were estimated as >99% conversion using differential scanning calorimetry:

- @ 100 °C, 35 minutes
- @ 125 °C, 23 minutes
- @ 150 °C, 16 minutes

TYPICAL PROPERTIES OF CURED MATERIAL

Cured for 30 minutes @ 125 °C.

Physical Properties:

Coefficient of Thermal Expansion, ISO 11359-2, K ⁻¹ :	
Pre Tg (Alpha 1)	62×10 ⁻⁶
Post Tg (Alpha 2)	193×10 ⁻⁶
Glass Transition Temperature, ASTM E 228, °C	56
Shore Hardness, ISO 868, Durometer D	≥70 ^{LMS}
Linear Shrinkage, ASTM D 792, %	1.4
Water Absorption, ISO 62, %:	
2 hours in boiling water	1.8
7 days in water @ 22 °C	0.63
Elongation, at break, ISO 527-3, %	2.98
Tensile Strength, ISO 527-3	N/mm ² 62 (psi) (8,970)
Tensile Modulus, ISO 527-3	N/mm ² 2,383 (psi) (345,500)

TYPICAL PERFORMANCE OF CURED MATERIAL

Adhesive Properties

Cured for 30 minutes @ 120 °C.

Lap Shear Strength, ISO 4587:

Aluminum (etched):	
0.125 mm gap	N/mm ² ≥13.8 ^{LMS} (psi) (≥2,000)

Cured for 30 minutes @ 100 °C.

Needle Pullout Strength:

Material	22 Gauge Cannula	27 Gauge Cannula:
ABS	N 302 (lb) (68)	N 147 (lb) (33)
Acrylic	N 276 (lb) (62)	N 142 (lb) (32)
Polycarbonate	N 89 (lb) (20)	N 76 (lb) (17)
Polyethylene	N 13 (lb) (3)	N 13 (lb) (3)
Polyethylene (plasma treated)	N 214 (lb) (48)	N 138 (lb) (31)
Polypropylene	N 18 (lb) (4)	N 13 (lb) (3)
Polypropylene (plasma treated)	N 160 (lb) (36)	N 98 (lb) (22)
Polystyrene	N 191 (lb) (43)	N 125 (lb) (28)
Polyurethane	N 280 (lb) (63)	N 151 (lb) (34)

Cured for 30 minutes @ 125 °C.

Block Shear Strength, ISO 13445:

Acrylic	N/mm ² 4 (psi) (580)
G-10 Epoxy	N/mm ² 15 (psi) (2,240)
Nylon	N/mm ² 4 (psi) (620)
Polybutylene Terephthalate	N/mm ² 12 (psi) (1,670)
Polycarbonate	N/mm ² 3 (psi) (370)
Aluminum (grit blasted)	N/mm ² 29 (psi) (4,160)
Steel (grit blasted)	N/mm ² 34 (psi) (4,930)

TYPICAL ENVIRONMENTAL RESISTANCE

Thermal Stability of Needle Assemblies

Aged @ 60°C and tested @ 22 °C

Needle Pullout Strength, % initial strength retained:

Plastic:	4 Weeks	8 Weeks:
Polycarbonate:		
22 Gauge Cannula	255	290
27 Gauge Cannula	175	205
Polypropylene (plasma treated):		
22 Gauge Cannula	170	180
27 Gauge Cannula	170	160
Polystyrene:		
22 Gauge Cannula	125	110
27 Gauge Cannula	120	125

Sterilization Resistance of Needle Assemblies

Sterilized as indicated and tested @ 22 °C

Needle Pullout Strength, % initial strength retained:


Plastic	Gamma 30 kGy	ETO 1 cycle	Autoclave 1 cycle 5 cycles	
Polycarbonate:				
22 Gauge Cannula	110	110	90	90
27 Gauge Cannula	100	100	60	75
Polypropylene (plasma treated):				
22 Gauge Cannula	145	140	75	85
27 Gauge Cannula	140	110	65	100
Polystyrene:				
22 Gauge Cannula	100	100	N/A	N/A
27 Gauge Cannula	95	90	N/A	N/A

N/A - Not Applicable. The polystyrene was not compatible with the autoclave sterilization process.

Hot Strength

Cured for 30 minutes @ 125 °C. The bonded specimens were tested at the indicated temperature:


Block Shear Strength, ISO 13445, Polycarbonate



Heat Aging

Cured for 30 minutes @ 125 °C. The bonded specimens were conditioned as indicated and tested at 22 °C.

Block Shear Strength, ISO 13445, Polycarbonate



Chemical/Solvent Resistance

Cured for 30 minutes @ 125 °C. The bonded specimens were conditioned as indicated and tested at 22 °C.

Block Shear Strength, ISO 13445, Polycarbonate

Environment	°C	% of initial strength			
		24 h	100 h	500 h	1000 h
95% RH	40	-----	140	170	170
Ambient Water Submersion	22	-----	160	160	115
Isopropanol	22	150	-----	-----	-----
Heptane	22	140	-----	-----	-----

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

Directions for use:

1. Adhesive must be room temperature just prior to use.
2. Clean and dry surfaces to be bonded.
3. Apply adhesive evenly to both surfaces.
4. Assemble parts and allow to cure at 100 °C for 35 minutes or until completely firm.
5. Refer to cure schedule for alternate cure information.

Loctite Material Specification^{LMS}

LMS dated August 08, 2002. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Quality.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 2 °C to 8 °C. Storage below 2 °C or greater than 8 °C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\mu\text{m} / 25.4 = \text{mil}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive

use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1.1